

AN 1992:134551 CAPLUS
 DN 116:134551
 TI Processing of copper alloys for high strength, electric conductivity, and
 bendability
 IN Hirano, Yasuo
 PA Nippon Mining Co., Ltd., Japan
 SO Jpn. Kokai Tokkyo Koho, 6 pp.
 CODEN: JKXXAF

DT Patent
 LA Japanese
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
	-----	----	-----	-----	-----
PI	JP 03162553	A2	19910712	JP 1989-302005	19891122
PRAI	JP 1989-302005		19891122		

AB Cu-(0.4-4.0) Ni-(0.1-1.0)% Si alloys are
 soln. treated at $\geq 700^\circ$ for grain size 1-10 μm ,
 cold rolled at draft $< 40\%$, and aged at $300-700^\circ$ to increase
 strength, elec. cond, and bendability. The alloys optionally contain
 0.001-2.0% of Fe, Mg, Al, Cr, Mn, Co, Zn, Ti, Zr, Pb, Cd, In, Ag, and/or
 P, and are used for elec. applications. Thus, a Cu-1.6
 Ni-0.4% Si alloy processed according to the invention
 showed tensile strength 55 kg/mm², elongation 15%, and elec. conductivity 50%

of
 Cu standard